

SPC CLICK FLOORING

STONE

Dimension 610 x 305mm

Construction New Generation of Luxury Vinyl Tiles, mixture by Natural

Limestone Powder, polyvinyl chloride, stabilizer etc.

Density 2000kg/m³

Thickness 4.0mm

Wear Classification 0.3mm

Surface structure Mat Surface

Edge type Mrcro bevel available

Locking system Click installed

| Properties | Test Method | Unit | Test Result | | Remarks |
|------------------------------------|---|--------|---|------|---|
| Dimensional stability | With reference to BS EN ISO 23999:2012 | % | Manufacturing direction | 0.06 | Heating temperature: 80 ℃ Heating time: 6h |
| | | | Across-manufacturing direction | 0.03 | |
| Curling after exposure to heat | | mm | 0 | | ricuting time. on |
| Peel Resistance | BS EN ISO 24345:2012 | N/50mm | Machine direction | 80 | Loading rate: 100mm/min |
| | | | Across machine | 75 | |
| Reisdual indentation | EN ISO 24343-1:2012 | mm | 0.06 | | |
| Staining and resistance to chemica | EN ISO 26987:2012 | / | not affected | | |
| Wear resistance | EN 660-2: 1999+A1:2003 and EN | 1 | Wear group: T | | |
| Color fastness to light | EN ISO 105-B02:2014 | / | Grade (Bluewood Std) 6 | | |
| Effect of a castor chair | EN 425:2002 | 1 | No visible damage | | Cycles:25000, load: 90kg |
| Slip resistance | DIN 51130:2014-02 | 1 | Critical angle of inclination: 1 | R10 | |
| RoHS Directive 2011/65/EU | IEC 62321 | | Not Detected | | |
| Phthalates | EN14372:2004 | | Not Detected | | |
| REACH | Regulation (EC) No 1907/2016 REACH | % | According to the specified scope and evaluation screening, the test results of SVHC are less than 0.1%(w/w) | | 169 Substances of Very High Concern(SVHC) for authorization by European Chemicals Agency(ECHA) on and before Jun 20,2016 were Not Detected. |